

06-30-00

A

LIMBACH & LIMBACH L.L.P.
2001 Ferry Building, San Francisco, CA 94111
415/433-4150

Address to:

Box Patent Application
Assistant Commissioner for Patents
Washington, D.C. 20231

Attorney's Docket No. SONY-T0850

First Named Inventor YUJI KURODA

UTILITY PATENT APPLICATION TRANSMITTAL

(under 37 CFR 1.53(b))

SIR:

Transmitted herewith for filing is the patent application entitled:

OPTICAL RECORDING MEDIUM AND OPTICAL RECORDING AND REPRODUCTION DEVICE

CERTIFICATION UNDER 37 CFR § 1.10

I hereby certify that this New Application and the documents referred to as enclosed herein are being deposited with the United States Postal Service on this date June 29, 2000, in an envelope bearing "Express Mail Post Office To Addressee" Mailing Label Number EL254155235US addressed to: Box Patent Application, Assistant Commissioner for Patents, Washington, D.C. 20231.

Elizabeth Reicker

(Name of person mailing paper)

Elizabeth Reicker
(Signature)

Enclosed are:

1. ☒ Transmittal Form (two copies required)
2. The papers required for filing date under CFR § 1.53(b):
 - i. 41 Pages of specification (including claims and abstract);
 - ii. 6 Sheets of drawings.

☒ formal ☐ informal
3. Declaration or oath
 - a. ☒ Unsigned

ACCOMPANYING APPLICATION PARTS

4. ☐ An assignment of the invention to Sony Corporation is attached (including Form PTO-1595).
 - i. ☐ 37 CFR 3.73(b) Statement (when there is an assignee)
5. ☒ Power of Attorney (unsigned)
6. ☐ An Information Disclosure Statement (IDS) is enclosed, including a PTO-1449 and copies of ☐ references.
7. ☐ Preliminary Amendment.
8. ☒ Return Receipt Postcard (MPEP 503 -- should be specifically itemized)
9. FOREIGN PRIORITY

[x] Priority of application no. P11-196746 filed on July 9, 1999 in Japan is claimed under 35 USC 119.

The certified copy of the priority application:

- ☒ is filed herewith; or
- ☐ has been filed in prior application no. ☐ filed on ☐, or
- ☐ will be provided.

☐ English Translation Document (if applicable)



06/29/00 09/606885

10. FEE CALCULATION

- a. ☐ Amendment changing number of claims or deleting multiple dependencies is enclosed.

CLAIMS AS FILED

	Number Filed	Number Extra	Rate	Basic Fee (\$690)
Total Claims	58 - 20	* 38	x \$18.00	684.00
Independent Claims	4 - 3	* 1	x \$78.00	78.00
<input type="checkbox"/> Multiple dependent claim(s), if any			\$260.00	0

*If less than zero, enter "0".

Filing Fee Calculation \$1,452.00

50% Filing Fee Reduction (if applicable) \$

11. Small Entity Status

- a. ☐ A small entity statement is enclosed.
b. ☐ A small entity statement was filed in the prior nonprovisional application and such status is still proper and desired.
c. ☐ is no longer claimed.

12. Other Fees

- ☐ Recording Assignment [\$40.00] \$0
☐ Other fees
Specify _____ \$0

Total Fees Enclosed \$1,452.00

13. Payment of Fees

- ☒ Check(s) in the amount of \$ 1,452.00 enclosed.
☐ Charge Account No. 12-1420 in the amount of \$ ____.
A duplicate of this transmittal is attached.

14. All correspondence regarding this application should be forwarded to the undersigned attorney:

Charles P. Sammut
Limbach & Limbach L.L.P.
2001 Ferry Building
San Francisco, CA 94111
Telephone: 415/433-4150
Facsimile: 415/433-8716


15. Authorization to Charge Additional Fees

- ☒ The Commissioner is hereby authorized to charge any additional fees (or credit any overpayment) associated with this communication and which may be required under 37 CFR § 1.16 or § 1.17 to Account No. 12-1420. **A duplicate of this transmittal is attached.**

LIMBACH & LIMBACH L.L.P.

June 29, 2000
(Date)

Attorney Docket No. SONY-T0850
[S00P0850US00]

By: 
Charles P. Sammut
Registration No. 28,901
Attorney(s) or Agent(s) for Applicant(s)

OPTICAL RECORDING MEDIUM AND

OPTICAL RECORDING AND REPRODUCTION DEVICE

BACKGROUND OF THE INVENTION

5 1. Field of the Invention

 The present invention relates to an optical
recording medium and an optical recording and
reproduction device, more particularly an optical
recording medium used at a near field which is able to
10 prevent heat buildup at the surface of the optical
recording medium due to focusing of light when recording
or reproducing and the consequent signal loss or damage
to the optical recording medium and an optical recording
and reproduction device including the same.

15 2. Description of the Related Art

 Up to now, a hard disk or other magnetic
recording medium has been used in a state with a head for
recording and reproduction brought into extremely close
20 proximity to the disk or other medium for the purpose of
obtaining good signal characteristics. As opposed to
this, a phase change type optical disk, magneto-optical
disk, or other optical recording medium is used in a
state with the optical system or head for recording and
25 reproduction separated from the recording medium by a

predetermined distance.

However, in recent years, in the devices used for optical recording media, the system of bringing the optical system or head into close proximity, for example, 200 nm with the disk (near field) has begun to be employed for the purpose of increasing a numerical aperture (NA) of the optical system and thereby increasing a recording density of the disk.

As an optical recording medium device used at the near field, for example, there are an optical hard disk structured with a lens mounted on a slider, an optical disk device with a lens made movable by an electromagnetic actuator, etc. In these devices, light for recording and reproduction is focused on the recording medium by an optical system comprised of a plurality lenses including at least an objective lens and a solid immersion lens (SIL). Due to this, an NA of over 1 has been obtained.

Figure 1 is a schematic view of a hard disk. The disk 11 is structured with a recording layer 13 and a lubrication film 14 stacked on a substrate 12. A recording and reproducing head 15 for changing the magnetization of the recording layer 13 is mounted on a slider 16 and movable in the direction of the disk plane. The lubrication film 14 is provided for preventing

abrasion of the head 15 and the disk 11. The lubrication film 14 is formed, for example, by coating a fluorine compound. In the case of an optical disk, consideration of optical conditions is required for a layer formed on a recording layer, but the lubrication film 14 of a hard disk does not require consideration of optical conditions. Therefore, it can be relatively easily formed.

Figure 2 is a schematic view of an optical disk with a long distance between an optical system or head and the disk (far-field optical disk). The optical disk of Fig. 2 is for example a phase change type optical disk or a magneto-optical disk and is structured with a dielectric protective layer 22, a recording layer 23, a dielectric protective layer 24, a reflective film 25, and a resinous protective layer 26 sequentially stacked on a substrate 21.

In the case of a phase change type optical disk, a material changing in phase by focusing of light is used for the recording layer 23. Both surfaces of the recording layer 23 are protected by the dielectric protective layers 22, 24 comprised of for example ZnS-SiO₂. These surfaces are further protected by the substrate 21 or the resinous protective layer 26.

In the case of a magneto-optical disk, a

material changing in magnetization state by focusing of light is used for the recording layer 23.

5 The optical disk of Fig. 2 has a much longer distance between a lens 27 and the disk than that of a hard disk. A film for dealing with friction or collision between the lens 27 (or head) and the disk is usually preferable, but not necessary.

10 Figure 3 is a cross-sectional view of an optical disk used in the near field. It is structured by a reflective layer 32, a second dielectric layer 33, a recording layer 34, and a first dielectric layer 35 sequentially stacked on a substrate 31. In the case of the optical disk shown in Fig. 2, light is focused from the side at which the transparent substrate 21 is formed. 15 On the other hand, in the case of the optical disk for near-field use shown in Fig. 3, light is focused from the side at which the first dielectric layer 35 is formed. Due to this, the increase in the coma along with an increase in the NA is moderated.

20 In the optical disk of Fig. 3, the four layers of the first dielectric layer 35, the recording layer 34, the second dielectric layer 33, and the reflective layer 32 are optimized in design for obtaining good signal characteristics for light striking the disk 25 surface perpendicularly.

On the other hand, in the case of a near-field optical disk device having a short distance between the head and the disk as described above, the risk of collision of the lens and the rest of the optical system (or head) with the disk becomes extremely high. However, it is very difficult to uniformly coat a lubricating substance such as used for the lubrication film 14 of the hard disk on the surface of an optical disk to form a thin film satisfying the optical conditions. Also, in the case of a near-field configuration, the fluorine material used for the lubrication film 14 of a hard disk cannot be used because the refractive index is too low. There are few other suitable materials.

When an AR coating is provided on the surface of the lens, once the AR (Antireflecting) coating at the lens side is damaged due to collision, the recording and reproduction influenced by the damage at all times. That is, a change of the optical characteristics of the entire device is caused. However, it is difficult to find a suitable coating material resistant to damage by collision as the material for the AR coating.

Further, according to the conventional near-field optical disk shown in Fig. 3, as the protective layers 33, 35 of the recording layer 34, a ZnS-SiO₂ layer having a low heat conductivity is often formed.

Therefore, when focusing laser light at the time of recording and/or reproduction, heat builds up between the optical system and the recording layer. The heat causes the problems of loss of signals recorded on the optical disk or damage to the disk itself.

Figure 4A shows a result of calculating the temperature rise due to focusing of laser light when making the optical disk the film configuration shown in Fig. 3. In Fig. 4A, the temperature of the recording layer is plotted against time after focusing of the laser light. As shown in Fig. 4B, the disk surface was set as an x-y plane, the beam spot was set as the origin O, and the direction of the optical axis of the laser light was set as a z-axis. The direction x of beam travel is the direction of relative movement of the beam spot on the disk along with disk rotation. Therefore, y corresponds to a distance from the beam spot in the direction of the disk radius. The calculation was performed setting y as 0 nm, 300 nm, and 500 nm. The intensity of the laser light was assumed to be 0.2 mW or the same level as the reproducing light.

The specific film configuration was made as follows (below, this film configuration is used as a comparative example for the present invention). The reflective layer 32 was made an Al-alloy layer of a

thickness of 120 nm. The second dielectric layer 33 was made a ZnS-SiO₂ layer having a refractive index $n=2$ and a thickness of 20 nm. The recording layer 34 was made a Ge-Sb-Te layer having a refractive index $n=3.9$, a quenching coefficient $k=3.5$, and a thickness of 20 nm. The first dielectric layer 35 was made a ZnS-SiO₂ layer having a refractive index $n=2$ and a thickness of 100 nm. An optical system (lens) arranged in proximity to the optical disk was made a refractive index $n=1.8$.

As shown in Fig. 4A, although the intensity of the laser light is sufficiently smaller than the intensity of the recording light, the recording layer reaches a high temperature. Also, during a certain time until the rising temperature goes down, heat is built up at the recording layer.

Generally, it is necessary to reduce the distance between the lens and the disk for increasing the reproduced signal level. When a recording and reproducing system, in which the lens and the disk are brought into extremely close proximity, is used, the recording layer is easily damaged due to collision of the lens with the surface of the disk.

However, according to the configuration shown in Fig. 3, the first dielectric layer 35, that is, a thin layer of for example ZnS-SiO₂ or SiN, is formed on the

outermost layer of the disk. Therefore, when the lens and the disk collide, the first dielectric layer 35 and the recording layer 34 below the layer 35 are readily damaged.

5 Also, when only the extremely thin first dielectric layer 35 is formed on the recording layer 34, local light absorption easily occurs at the surface of the disk. If ablation occurs due to laser light at the time of recording or reproduction, the disk will be
10 damaged and the lens contaminated by the deposition of the disk material on the lens surface.

OBJECTS AND SUMMARY OF THE INVENTION

15 An object of the present invention is to provide an optical recording medium used in the near field and able to prevent heat buildup due to the focusing of laser light and the consequent loss of signals recorded on the optical recording medium and damage to the optical recording medium and an optical recording and
20 reproduction device including the medium.

 Another object of the present invention is to provide an optical recording medium used for the near field and preventing damage due to collision with an optical system and an optical recording and reproduction
25 device including the medium.

According to a first aspect of the present invention, there is provided an optical recording medium comprising a substrate; a recording layer formed on the substrate; a first protective layer formed on the recording layer; and a transparent heat radiating layer formed on the first protective layer for promoting dispersion of heat from the recording layer; light being exposed on the recording layer via a side at which the heat radiating layer is positioned to thereby perform recording and/or reproduction of information.

Preferably, said optical recording medium is used in near field condition. Preferably, the near field condition comprises a space between the heat radiating layer and an optical system of about 200 nm or less. Preferably, the optical system comprises a solid immersion lens (SIL).

Preferably, the heat radiating layer has a higher heat conductivity than the first protective layer. More preferably, the heat radiating layer has a heat conductivity of about 0.1 (W/cm·K) or more.

More preferably, the heat radiating layer has a quenching coefficient with respect to the light used for recording and reproducing of less than about 0.1.

Preferably, the heat radiating layer comprises at least one of BN, AlN, SiN, SiC, Ta₂O₅, and diamond-state

carbon.

Preferably, the heat radiating layer comprises a multilayer film comprising a plurality layers having substantially same optical constants and having different heat constants stacked together. Preferably, a light reflecting layer comprised of metal or semimetal is formed between the substrate and the recording layer. Preferably, the optical recording medium further comprises an antireflection layer on the heat radiating layer. Preferably, the optical recording medium further comprises an antireflection layer between the heat radiating layer and the recording layer.

Preferably, the optical recording medium further comprises a second protective layer between the substrate and the recording layer.

Preferably, the recording layer comprises a material undergoing a phase change and changing in a complex index of refraction due to the focusing of light.

Alternatively, the recording layer preferably comprises a material changing in a magnetization state by using the focusing of light and enabling detection of the change as a change of a polarization state.

Alternatively, the recording layer preferably changes in a complex index of refraction or shape due to light with respect to the wavelength of the reproducing

light.

Due to this, heat built up at the recording layer due to the focusing of laser light is dispersed to the surface of the optical recording medium via the heat radiating layer. Therefore, it is possible to prevent a rise in temperature at the surface of the optical recording medium due to focusing of laser light. Due to this, it is possible to maintain the signals recorded on the optical recording medium and prevent damage to the optical recording medium due to heat.

Also, according to the optical recording medium of the present invention, a layer comprised of Al or other inorganic material is formed at the outermost layer of the optical recording medium as the heat radiating layer. Therefore, the surface hardness is high and the recording layer of the optical recording medium is resistant to damage even when a head or optical system and the optical recording medium collide.

Further, according to the optical recording medium of the present invention, by forming the heat radiating layer covering the surface of the optical recording medium, ablation of the material comprising the optical recording medium is prevented and destruction of the film along with the elapse of time due to ablation can be prevented. Therefore, the long-term reliability of the

optical recording medium can be improved.

Also, in the optical recording medium of the present invention, by making the heat radiating layer multilayer and suitably controlling the thicknesses of layers comprising the heat radiating layer, it becomes possible to control the optical characteristics and the heat characteristics of the heat radiating layer at the same time.

According to a second aspect of the present invention, there is provided an optical recording and reproduction device comprising a light source, an optical recording medium, and an optical system for focusing light from the light source on the optical recording medium, characterized in that the optical recording medium comprises a substrate, a recording layer formed on the substrate, a first protective layer formed on the recording layer, and a heat radiating layer formed on the first protective layer, that light from the optical system is exposed to the recording layer via a side with the heat radiating layer formed for recording and reproducing information, and that the heat radiating layer promotes dispersion of heat from the recording layer.

Preferably, a space between the heat radiating layer and the optical system comprises a near field. More

preferably, the space is about 200 nm or less. More preferably, the optical system comprises a solid immersion lens (SIL).

5 Preferably, the heat radiating layer has a higher heat conductivity than the first protective layer. More preferably, the heat radiating layer has a heat conductivity of about 0.1 (W/cm·K) or more. More preferably, the heat radiating layer has a quenching coefficient with respect to the light used for recording and reproducing of less than about 0.1.

10 Preferably, the heat radiating layer comprises at least one of BN, AlN, SiN, SiC, Ta₂O₅, and diamond-state carbon.

15 Preferably, the heat radiating layer is a multilayer film comprising a plurality of layers having substantially same optical constants and having different heat constants stacked together. Preferably, a light reflecting layer comprising metal or semimetal is formed between the substrate and the recording layer.

20 Preferably, the optical recording and reproduction device further comprises an antireflection layer on the heat radiating layer in the optical recording medium.

25 Preferably, the optical recording and reproduction device further comprises an antireflection layer between the heat radiating layer and the recording layer in the

optical recording medium.

Preferably, the optical recording and reproduction device further comprises a second protective layer between the substrate and the recording layer in the optical recording medium.

Preferably, the recording layer comprises a material undergoing a phase change and changing in a complex index of refraction due to light.

Alternatively, the recording layer preferably comprises a material changing in a magnetization state by using light and enabling detection of the change as a change of a polarization state.

Alternatively, the recording layer preferably comprises an organic dye material changing in a complex index of refraction or shape due to light with respect to a wavelength of the reproducing light.

Due to this, a rise in temperature of the optical recording medium due to focusing of laser light can be prevented and it is made possible to maintain signals recorded on the optical recording medium and prevent damage to the optical recording medium due to heat.

Also, since the heat radiating layer is formed at the outermost layer of the optical recording medium, the surface hardness becomes high and the optical recording medium is resistant to damage when a head or optical

system and the optical recording medium collide. Also, ablation due to focusing of laser light is also prevented. Therefore, it is possible to improve the long-term reliability of the optical recording and reproduction device.

Also, when an antireflection film is formed on the optical recording medium used for the optical recording and reproduction device of the present invention, it becomes unnecessary to provide an antireflection coating on the surface of the optical system. Therefore, it is possible to prevent damage of the antireflection coating and an effect on recording and reproduction.

According to a third aspect of the present invention, there is provided an optical recording and reproduction device comprising a light source, an optical recording medium, and an optical system focusing light from the light source to the optical recording medium, wherein the optical recording medium comprises a substrate, a phase change recording layer formed on the substrate and comprised of a material undergoing a phase change and changing in a complex index of refraction by said focusing of light, a first protective layer formed on the phase change recording layer, and a heat radiating layer formed on the first protective layer, light from the optical system is exposed to the phase change

recording layer via a side with the heat radiating layer formed for recording and reproducing information, and the heat radiating layer promotes dispersion of heat from the phase change recording layer.

5 According to a fourth aspect of the present invention, there is provided an optical recording and reproduction device comprising a light source, an optical recording medium, and an optical system focusing light from the light source to the optical recording medium, 10 wherein the optical recording medium comprises a substrate, a recording layer formed on the substrate, a first protective layer formed on the recording layer, and a heat radiating layer formed on the first protective layer, light is focused from the optical system 15 comprising a near field with the numerical aperture (NA) more than 1 to the recording layer via a side with the heat radiating layer formed for recording and reproducing information, and the heat radiating layer promotes dispersion of heat from the recording layer.

20

BRIEF DESCRIPTION OF THE DRAWINGS

These and other objects and features of the present invention will become clearer from the following description of the preferred embodiments given with 25 reference to the accompanying drawings, in which:

Fig. 1 is a schematic view of a magnetic recording device (hard disk) of related art;

Fig. 2 is a cross-sectional view of an optical recording medium of related art used in a state wherein the disk and the optical system are sufficiently separated;

Fig. 3 is a cross-sectional view of a near-field optical recording medium of related art;

Fig. 4A is a view of characteristics of the near-field optical recording medium of related art showing the temperature rise of the recording layer due to focusing of laser light and Fig. 4B is a coordinates defining each axis;

Fig. 5 is a schematic view of an arrangement of an optical recording medium of the first embodiment through the fourth embodiment of the present invention and an optical system;

Fig. 6 is a cross-sectional view of an optical recording medium of the first embodiment through the third embodiment of the present invention;

Fig. 7 is a view of the characteristic of the optical recording medium of the second embodiment of the present invention showing the temperature rise of the recording layer due to focusing of laser light;

Fig. 8 is a view of the characteristics of the

optical recording medium of the third embodiment of the present invention showing heat distribution from a recording mark on which laser light is focused in directions of the disk plane; and

5 Fig. 9 is a view of characteristics of an optical recording medium of a comparative example of the third embodiment of the present invention showing heat distribution from a recording mark on which laser light is focused in directions of the disk plane.

10 DESCRIPTION OF THE PREFERRED EMBODIMENTS

Below, embodiments of the optical recording medium and the optical recording and reproduction device of the present invention will be explained with reference to the drawings.

15 First, the first embodiment of the present invention will be explained. Figure 5 shows an arrangement of the optical recording medium of the present embodiment and an optical part (lens). As shown in Fig. 5, an optical disk 51 comprises a substrate 52 on which are formed stacked layers 53 including a recording layer. An SIL 54 is arranged at the stacked layer 53 side of the optical disk 51. The distance t between the surface of the stacked layers 53 and the SIL 54 is
20 extremely narrow, usually 200 nm or less. Since light
25

collected by an objective lens (not shown) enters the SIL 54, the NA becomes high. Also, θ represents the incident angle of the light focused on the optical disk 51.

Figure 6 is a cross-sectional view of the optical recording medium of the present embodiment. The present embodiment is assumed as a phase change type optical disk used for light of a wavelength of 650 nm. The optical disk shown in Fig. 6 is structured with a reflective layer 62, a second dielectric layer 63, a recording layer 64, and a first dielectric layer 65 sequentially stacked on a substrate 61 and, further, a heat radiating layer 66 formed on them.

On the optical disk of the present embodiment, laser light is focused from the side at which the heat radiating layer 66 is formed. The laser light strikes the optical disk with the line passing through the center of the beam diameter (beam waist) perpendicular to the surface of the disk.

In the optical disk of Fig. 6, the five layers of the heat radiating layer 66, the first dielectric layer 65, the recording layer 64, the second dielectric layer 63, and the reflective layer 62 satisfy an enhancement condition of the light perpendicularly striking the disk surface (perpendicularly incident component). The design is optimized for obtaining good signal characteristics

for the perpendicularly incident component.

According to the film configuration of the present embodiment, as the reflective layer 62, for example, an Al-alloy layer of a thickness of 120 nm is used. As the second dielectric layer 63, a ZnS-SiO₂ layer having a refractive index $n=2$ and a thickness of 20 nm is used. As the recording layer 64, a Ge-Sb-Te layer having a refractive index $n=3.9$, a quenching coefficient $k=3.5$, and a thickness of 20 nm is used. As the first dielectric layer 65, a ZnS-SiO₂ layer having a refractive index $n=2$ and a thickness of 50 nm is used. As the heat radiating layer 66, an AlN layer having a refractive index $n=2$ and a thickness of 50 nm is used. The optical system (lens) arranged next to the optical disk is made one with a refractive index $n=1.8$.

Below, each layer comprising the optical disk of the present embodiment will be explained in detail.

As the substrate 61, for example, a plastic substrate comprised of polycarbonate (PC) or polymethyl methacrylate (PMMA) and other acryl-based resins and a glass substrate etc. may be used.

As the reflective layer 62 on the substrate 61, for example an Al layer or Al-alloy layer is used. The thickness of the reflective layer 62 is set at, for example, about 50 to 200 nm. The reflective layer 62 not

only reflects the light focused on the optical disk, but also functions to promote the dispersion of heat from the recording layer 64. While the temperature of the recording layer 64 rises due to absorption of light, the reflective layer 62 has a high heat conductivity since it is usually composed of a metal layer and acts as a kind of heat sink. As the material of the reflective layer 62, as long as the material has a predetermined reflectance and heat conductivity, it is also possible to use a semimetal, a compound of metal or semimetal, and semiconductors and their compounds in addition to metal.

The second dielectric layer 63 functions as a protective layer of the phase changing recording layer 64. The second dielectric layer 63 need not necessarily be formed, for example, when not rewriting on the optical disk and in other cases.

As the recording layer 64 on the second dielectric layer 63, a material changing in phase reversibly between a crystal and amorphous state by focusing of a laser may be used. For example, chalcogens or chalcogen compounds, specifically, a system including Te, Se, Ge-Te, Ge-Sb-Te, Ge-Te Sb-Te, In-Sb-Te, Ag-In-Sb-Te, Au-In-Sb-Te, Ge-Sb-Te-Se, In-Sb-Se, Bi-Te, Bi-Se, Sb-Se, Sb-Te, Ge-Sb-Te-Bi, Ge-Sb-Te-Co, Ge-Sb-Te-Au, Zn-Ge-In-Sb-Te, or such a system doped with nitrogen, oxygen, or another gas

additive or doped with Pd can be mentioned.

The first dielectric layer 65 on the recording layer 64 functions as a protective layer of the phase changing recording layer 64.

5 For the heat radiating layer 66 on the first dielectric layer 65, a material having a higher heat conductivity than the first dielectric layer 65 is used. Specifically, a material having a heat conductivity of almost 0.1 (W/cm·K) or more and a quenching coefficient k of less than 0.1 with respect to the laser light used for recording and/or reproducing is preferably used. For example, BN, SiN, SiC, Ta₂O₅, diamond-state carbon, and mixtures of these can be preferably used as the material of the heat radiating layer 66, in addition to Al described above. Also, the thickness of the heat radiating layer 66 is appropriately set within a range where the heat radiating layer 66 has transparency.

10 According to the above optical recording medium of the present embodiment, since the heat radiating layer having a high heat conductivity is formed between the recording layer of the disk and the optical system, the temperature rise at the disk surface due to the focusing of laser light can be prevented. Due to this, it is made possible to maintain signals recorded on the optical disk and prevent damage to the optical disk by heat.

15

20

25

Also, according to the optical recording medium of the present embodiment, since a layer composed of AlN or another inorganic material is formed at the outermost layer of the disk as the heat radiating layer 66, the surface hardness is high and the recording layer of the optical disk is not easily damaged when the head or optical system and the disk collide.

According to the optical recording medium of the present embodiment, since the heat radiating layer 66 is formed covering the disk surface, ablation of the disk material is prevented and destruction of the film along with the elapse of time due to ablation can be prevented.

Also, when the optical recording medium of the present embodiment is combined with a light source and a near-field high NA optical system, the optical recording device of the present invention can be configured.

Next, the second embodiment of the present invention will be explained. Figure 7 shows the results of calculating the temperature rise in the phase change type optical disk of the above first embodiment due to focusing of laser light. In Fig. 7, the temperature of the recording layer is plotted against the time after the focusing of the laser light. As described above, the disk surface was made the x-y plane, the beam spot was made the origin O, and the direction of the optical axis of

the laser light was made the z-axis (see Fig. 4B). The direction x of beam travel is the direction of relative movement of the beam spot on the disk along with disk rotation. Therefore, y corresponds to the distance from the beam spot in the direction of disk radius. The calculation was performed setting y as 0 nm, 300 nm and 500 nm. The intensity of the laser light was presumed to be 0.2 mW or the same level as the reproducing light.

When comparing Fig. 7 with the case of the film configuration of Fig. 3 (see Fig. 4A), it is found that the maximum temperature reached by the recording layer is greatly lowered by forming the heat radiating layer 66. Also, along with this, the time until the rising temperature goes down is also shortened. Thus, the quantity of heat built up at the recording layer 66 is decreased.

As described above, since the temperature rise of the recording layer is suppressed, it is made possible to keep signals recorded on the optical disk and prevent damage to the optical disk due to heat.

Next, the third embodiment of the present invention will be explained. Figure 8 shows the results of calculating the dispersion of heat from a recording mark on which laser light is focused to directions in the disk plane (laser scanning direction or disk radius direction)

in the phase change type optical disk of the above first embodiment. For comparison, the results of calculation of the case of the configuration where the heat radiating layer 66 is not formed is shown in Fig. 9. The film configuration in the conventional structure is made the same as the comparative example described above (the conditions used for the calculation of Fig. 4A).

Figure 8 and Fig. 9 correspond to top views of the heat distribution of an optical disk. When comparing Fig. 8 with Fig. 9, it is found that the dispersion of heat in the disk radius direction is suppressed by the film configuration of the present embodiment. That is, in the case of the present embodiment, dispersion of heat in a direction perpendicular to the disk surface is promoted.

Therefore, according to the optical disk of the present embodiment, when laser light is focused on any recording mark, it is possible to prevent erasure of the recording mark formed in the next track, so-called, "cross write". Due to this, it is made possible to reduce the space between tracks and improve the recording density.

Also, when an optical disk having the configuration of the present invention was actually formed and tested, it was confirmed that the reliabilities of the recording marks and the recording layer were drastically improved

by forming the heat radiating layer.

Further, the fourth embodiment of the present invention will be explained. The heat radiating layer of the above optical disk of the present invention can also be a multilayer structure. By forming stacked layers comprised of a plurality of materials having extremely close optical constants and having different heat constants as the heat radiating layer, it is possible, in design, to control only the heat characteristics as desired while not changing the optical characteristics of the optical recording medium.

Also, in the film configuration of the optical recording medium of the first embodiment shown in Fig. 6, it is possible to form on the heat radiating layer 66 an antireflection film comprising for example a silicon oxide layer, silicon nitride layer, and silicon oxide layer sequentially stacked on each other. Alternatively, an antireflection film as described above can be formed between the first dielectric layer 65 and the heat radiating layer 66. When the antireflection film is formed in the optical recording medium, an antireflection coating on the surface of the lens becomes unnecessary. Due to this, it is possible to prevent damage to the antireflection coating on the lens surface caused by contact of the optical recording medium and the lens etc.

and the damage to the electric characteristics during recording and reproduction from the lens surface.

The embodiments of the optical recording medium and the optical recording and reproduction device of the present invention are not limited to the above explanation. For example, by forming by sputtering a layer of for example TbFeCo amorphous alloy or another material able to be changed in the magnetization state by using focusing of laser light, it is also possible to apply the present invention to a magneto-optical disk. Alternatively, it is also possible to apply the present invention to an optical disk using a dye in the recording layer. Also, the optical recording medium of the present invention can be either rewritable or read-only.

In addition, various modifications may be made within a range not outside the gist of the present invention.

Summarizing the effects of the present invention, according to the optical recording medium of the present invention, it is possible to prevent heat buildup in the optical recording medium due to focusing of laser light and the consequent erasure of signals recorded on the optical recording medium and damage to the optical recording medium.

Also, according to the optical recording and

reproduction device of the present invention, it is possible to prevent heat buildup in the optical recording medium due to focusing of laser light and the consequent erasure of signals recorded on the optical recording medium and damage to the optical recording medium.

Further, according to the optical recording medium of the present invention, it is possible to prevent damage due to collision with an optical system.

Also, according to the optical recording and reproduction device of the present invention, it is possible to prevent damage due to collision with an optical system.

What is claimed is:

1. An optical recording medium comprising:
a substrate;
a recording layer formed on the substrate;
5 a first protective layer formed on the
recording layer; and
a transparent heat radiating layer formed on
the first protective layer for promoting dispersion of
heat from the recording layer;
10 light being exposed on the recording layer
via a side at which the heat radiating layer is
positioned to thereby perform recording and/or
reproduction of information.
2. An optical recording medium as set forth in
15 claim 1, wherein said optical recording medium is used in
near field condition.
3. An optical recording medium as set forth in
claim 2, wherein the near field condition comprises
a space between the heat radiating layer and an optical
20 system of about 200 nm or less.
4. An optical recording medium as set forth in
claim 3, wherein the optical system comprises a solid
immersion lens (SIL).
- 25 5. An optical recording medium as set forth in
claim 1, wherein the heat radiating layer has a higher

heat conductivity than the first protective layer.

6. An optical recording medium as set forth in claim 5, wherein the heat radiating layer has a heat conductivity of about 0.1 (W/cm·K) or more.

5 7. An optical recording medium as set forth in claim 6, wherein the heat radiating layer has a quenching coefficient with respect to the light used for recording and reproducing of less than about 0.1.

10 8. An optical recording medium as set forth in claim 7, wherein the heat radiating layer comprises at least one of BN, AlN, SiN, SiC, Ta₂O₅, and diamond-state carbon.

15 9. An optical recording medium as set forth in claim 1, wherein the heat radiating layer is a multi-layer film comprising a plurality of layers having substantially same optical constants and having different heat constants stacked together.

20 10. An optical recording medium as set forth in claim 1, wherein a layer reflecting light and comprising metal or semimetal is formed between the substrate and the recording layer.

11. An optical recording medium as set forth in claim 1, further comprising an antireflection layer formed on the heat radiating layer.

25 12. An optical recording medium as set forth in

claim 1, further comprising an antireflection layer between the heat radiating layer and the recording layer.

13. An optical recording medium as set forth in claim 1, further comprising a second protective layer between the substrate and the recording layer.

14. An optical recording medium as set forth in claim 1, wherein the recording layer comprises a material undergoing a phase change and changing in a complex index of refraction by said light.

15. An optical recording medium as set forth in claim 1, wherein the recording layer comprises a material changing in a magnetization state by using said light and enabling detection of the change as a change of a polarization state.

16. An optical recording medium as set forth in claim 1, wherein the recording layer comprises an organic dye material changing in a complex index of refraction or shape by said light with respect to a wavelength of the reproducing light.

17. An optical recording and reproduction device comprising a light source, an optical recording medium, and an optical system focusing light from the light source to the optical recording medium, wherein

the optical recording medium comprises a substrate, a recording layer formed on the substrate, a

first protective layer formed on the recording layer, and
a heat radiating layer formed on the first protective
layer,

light from the optical system is exposed to
5 the recording layer via a side with the heat radiating
layer formed for recording and reproducing information,
and

said heat radiating layer promotes dispersion
of heat from the recording layer.

10 18. An optical recording and reproduction device
as set forth in claim 17, wherein a space between the
heat radiating layer and the optical system comprises a
near field.

15 19. An optical recording and reproduction device
as set forth in claim 18, wherein the space is about 200
nm or less.

20 20. An optical recording medium as set forth in
claim 19, wherein the optical system comprises a solid
immersion lens (SIL).

21. An optical recording and reproduction device
as set forth in claim 17, wherein the heat radiating
layer has a higher heat conductivity than the first
protective layer.

25 22. An optical recording and reproduction device
as set forth in claim 21, wherein the heat radiating

layer has a heat conductivity of about 0.1 (W/cm·K) or more.

23. An optical recording and reproduction device as set forth in claim 22, wherein the heat radiating
5 layer has a quenching coefficient with respect to the light used for recording and reproducing of less than about 0.1.

24. An optical recording and reproduction device as set forth in claim 23, wherein the heat radiating
10 layer comprises at least one of BN, AlN, SiN, SiC, Ta₂O₅, and diamond-state carbon.

25. An optical recording and reproduction device as set forth in claim 17, wherein the heat radiating
15 layer is a multi-layer film comprising a plurality of layers having substantially same optical constants and having different heat constants stacked together.

26. An optical recording and reproduction device as set forth in claim 17, wherein a layer reflecting the
20 light and comprising metal or semimetal is formed between the substrate and the recording layer.

27. An optical recording and reproduction device as set forth in claim 17, wherein said optical recording
medium further comprises an antireflection layer on the heat radiating layer.

25 28. An optical recording and reproduction device

as set forth in claim 17, wherein said optical recording medium further comprises an antireflection layer between the heat radiating layer and the recording layer.

29. An optical recording and reproduction device
5 as set forth in claim 17, wherein said optical recording medium further comprises a second protective layer between the substrate and the recording layer.

30. An optical recording and reproduction device
10 as set forth in claim 17, wherein the recording layer comprises a material changing in a magnetization state by using said light and enabling detection of the change as a change of a polarization state.

31. An optical recording and reproduction device
15 as set forth in claim 17, wherein the recording layer comprises an organic dye material changing in a complex index of refraction or shape by said light with respect to a wavelength of the reproducing light.

32. An optical recording and reproduction device
20 comprising a light source, an optical recording medium, and an optical system focusing light from the light source to the optical recording medium, wherein

the optical recording medium comprises a
substrate, a phase change recording layer formed on the
substrate and comprised of a material undergoing a phase
25 change and changing in a complex index of refraction by

said focusing of light, a first protective layer formed on the phase change recording layer, and a heat radiating layer formed on the first protective layer,

light from the optical system is exposed to
5 the phase change recording layer via a side with the heat radiating layer formed for recording and reproducing information, and

said heat radiating layer promotes dispersion of heat from the phase change recording layer.

10 33. An optical recording and reproduction device as set forth in claim 32, wherein a space between the heat radiating layer and the optical system comprises a near field.

15 34. An optical recording and reproduction device as set forth in claim 33, wherein the space is about 200 nm or less.

35. An optical recording medium as set forth in claim 34, wherein the optical system comprises a solid immersion lens (SIL).

20 36. An optical recording and reproduction device as set forth in claim 32, wherein the heat radiating layer has a higher heat conductivity than the first protective layer.

25 37. An optical recording and reproduction device as set forth in claim 36, wherein the heat radiating

layer has a heat conductivity of about 0.1 (W/cm·K) or more.

38. An optical recording and reproduction device as set forth in claim 37, wherein the heat radiating
5 layer has a quenching coefficient with respect to the light used for recording and reproducing of less than about 0.1.

39. An optical recording and reproduction device as set forth in claim 38, wherein the heat radiating
10 layer comprises at least one of BN, AlN, SiN, SiC, Ta₂O₅, and diamond-state carbon.

40. An optical recording and reproduction device as set forth in claim 32, wherein the heat radiating
15 layer is a multi-layer film comprising a plurality of layers having substantially same optical constants and having different heat constants stacked together.

41. An optical recording and reproduction device as set forth in claim 32, wherein a light reflecting
20 layer comprising metal or semimetal is formed between the substrate and the recording layer.

42. An optical recording and reproduction device as set forth in claim 32, wherein said optical recording medium further comprises an antireflection layer on the heat radiating layer.

25 43. An optical recording and reproduction device

as set forth in claim 32, wherein said optical recording medium further comprises an antireflection layer between the heat radiating layer and the recording layer.

5 44. An optical recording and reproduction device as set forth in claim 32, wherein said optical recording medium further comprises a second protective layer between the substrate and the recording layer.

10 45. An optical recording and reproduction device comprising a light source, an optical recording medium, and an optical system focusing light from the light source to the optical recording medium, wherein

15 the optical recording medium comprises a substrate, a recording layer formed on the substrate, a first protective layer formed on the recording layer, and a heat radiating layer formed on the first protective layer,

20 light is focused from the optical system comprising a near field with the numerical aperture (NA) more than 1 to the recording layer via a side with the heat radiating layer formed for recording and reproducing information, and

 said heat radiating layer promotes dispersion of heat from the recording layer.

25 46. An optical recording medium as set forth in claim 45, wherein the optical system comprises a solid

immersion lens (SIL).

47. An optical recording and reproduction device as set forth in claim 45, wherein the heat radiating layer has a higher heat conductivity than the first protective layer.

48. An optical recording and reproduction device as set forth in claim 47, wherein the heat radiating layer has a heat conductivity of about 0.1 (W/cm·K) or more.

49. An optical recording and reproduction device as set forth in claim 48, wherein the heat radiating layer has a quenching coefficient with respect to the light used for recording and reproducing of less than about 0.1.

50. An optical recording and reproduction device as set forth in claim 49, wherein the heat radiating layer comprises at least one of BN, AlN, SiN, SiC, Ta₂O₅, and diamond-state carbon.

51. An optical recording and reproduction device as set forth in claim 45, wherein the heat radiating layer is a multi-layer film comprising a plurality of layers having substantially same optical constants and having different heat constants stacked together.

52. An optical recording and reproduction device as set forth in claim 45, wherein a layer reflecting the

light and comprising metal or semimetal is formed between the substrate and the recording layer.

53. An optical recording and reproduction device as set forth in claim 45, wherein said optical recording medium further comprises an antireflection layer on the heat radiating layer.

54. An optical recording and reproduction device as set forth in claim 45, wherein said optical recording medium further comprises an antireflection layer between the heat radiating layer and the recording layer.

55. An optical recording and reproduction device as set forth in claim 45, wherein said optical recording medium further comprises a second protective layer between the substrate and the recording layer.

56. An optical recording and reproduction device as set forth in claim 45, wherein the recording layer comprises a material undergoing a phase change and changing in a complex index of refraction by said light.

57. An optical recording and reproduction device as set forth in claim 45, wherein the recording layer comprises a material changing in a magnetization state by using said light and enabling detection of the change as a change of a polarization state.

58. An optical recording and reproduction device as set forth in claim 45, wherein the recording layer

comprises an organic dye material changing in a complex index of refraction or shape by said light with respect to a wavelength of the reproducing light.

OPTICAL RECORDING MEDIUM AND
OPTICAL RECORDING AND REPRODUCTION DEVICE

5

ABSTRACT OF THE DISCLOSURE

An optical recording medium and an optical
recording and reproduction device including the same,
10 wherein the optical recording medium comprises a
substrate, a reflective layer formed on the substrate, a
recording layer formed on the reflective layer, a first
protective layer formed on the recording layer and a
transparent heat radiating layer formed on the first
15 protective layer for promoting dispersion of heat from
the recording layer, and light is focused on the
recording layer from an optical system via a side at
which the first protective layer is formed to prevent
heat buildup, erasure of recorded signals and damage to
20 the optical recording medium.

FIG. 1




FIG. 2




FIG. 3




FIG. 4A




FIG. 4B




FIG. 5




FIG. 6




FIG. 7




FIG. 8





FIG. 9



SONY-T0850

BY EXPRESS MAIL NO. EL254155235US

Declaration and Power of Attorney For Patent Application

特許出願宣言書及び委任状

Japanese Language Declaration

日本語宣言書

下記の氏名の発明者として、私は以下の通り宣言します。	As a below named inventor, I hereby declare that:
私の住所、私書箱、国籍は下記の私の氏名の後に記載された通りです。	My residence, post office address and citizenship are as stated next to my name.
下記の名称の発明に関して請求範囲に記載され、特許出願している発明内容について、私が最初かつ唯一の発明者（下記の氏名が一つの場合）もしくは最初かつ共同発明者であると（下記の名称が複数の場合）信じています。	I believe I am the original, first and sole inventor (if only one named is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled.
	OPTICAL RECORDING MEDIUM AND OPTICAL RECORDING AND REPRODUCTION DEVICE
上記発明の明細書（下記の欄でx印がついていない場合は、本書に添付）は、 <input type="checkbox"/> 月 日に提出され、米国出願番号または特許協定条約国際出願番号を _____ とし、 （該当する場合） _____ に訂正されました。	the specification of which is attached hereto unless the following box is checked: <input type="checkbox"/> was filed on _____ as United States Application Number or PCT International Application Number _____ and was amended on _____ (if applicable).
私は、特許請求範囲を含む上記訂正後の明細書を検討し、内容を理解していることをここに表明します。	I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.
私は、連邦規則法典第37編第1条56項に定義されるとおり、特許資格の有無について重要な情報を開示する義務があることを認めます。	I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56.
私は、米国法典第35編119条(a)-(d)項又は365条(b)項に基づき下記の、米国以外の国の少なくとも一カ国を指定している特許協力条約365(a)項に基づく国際出願、又は外国での特許出願もしくは発明者証の出願についての外国優先権をここに主張するとともに、優先権を主張している、本出願の前に出願された特許または発明者証の外国出願を以下に、枠内をマークすることで、示しています。	I hereby claim foreign priority under Title 35, United States Code, Section 119(a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed.
Prior Foreign Application(s) 外国での先行出願 P11-196746 (Number) (番号)	Priority Not Claimed 優先権主張なし 9 July 1999 (Day/Month/Year Filed) (出願年月日)
Japan (Country) (国名)	

Japanese Language Declaration

日本語宣言書

(Number) _____ (番号) _____		(Country) _____ (国名) _____		(Day/Month/Year Filed) _____ (出願年月日) _____	
私は、第35編米国法典119条(e)項に基いて下記の米 国特許出願規定に記載された権利をここに主張いたします。		I hereby claim the benefit under Title 35, United States Code, Section 119(e) of any United States provisional application(s) listed below.			
(Application No.) _____ (出願番号) _____		(Filing Date) _____ (出願日) _____		(Application No.) _____ (出願番号) _____	
(Filing Date) _____ (出願日) _____		(Filing Date) _____ (出願日) _____			
私は、下記の米国法典第35編120条に基いて下記の米 国特許出願に記載された権利、又は米国を指定している特許 協力条約365条(c)に基づき権利をここに主張します。また、 本出願の各請求範囲の内容が米国法典第35編112条 第1項又は特許協力条約で規定された方法で先行する米国特 許出願に開示されていない限り、その先行米国出願書提出日 以降で本出願書の日本国内または特許協力条約国際提出日ま での期間中に入手された、連邦規則法典第37編1条56項 で定義された特許資格の有無に関する重要な情報について開 示義務があることを認識しています。		I hereby claim the benefit under Title 35, United States Code, Section 120 of any United States application(s), or 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code, Section 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of application.			
(Application No.) _____ (出願番号) _____		(Filing Date) _____ (出願日) _____		(Status: Patented, Pending, Abandoned) (現況: 特許許可済、係属中、放棄済)	
(Application No.) _____ (出願番号) _____		(Filing Date) _____ (出願日) _____		(Status: Patented, Pending, Abandoned) (現況: 特許許可済、係属中、放棄済)	
私は、私自身の知識に基づいて本宣言書中で私が行なう表 明が真実であり、かつ私の入手した情報と私の信じるところ に基づく表明が全て真実であると信じていること、さらに故 意になされた虚偽の表明及びそれと同等の行為は米国法典第 18編第1001条に基づき、罰金または拘禁、もしくはそ の両方により処罰されること、そしてそのような故意による 虚偽の声明を行なえば、出願した、又は既に許可された特許 の有効性が失われることを認識し、よってここに上記のごと く宣誓を致します。		I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may be jeopardize the validity of the application or any patent issued thereon.			

Japanese Language Declaration

日本語宣言書

委任状： 私は下記の発明者として、本出願に関する一切の手続きを米特許商標局に対して遂行する弁理士または代理人として、下記の者を指名いたします。（弁理士、または代理人の氏名及び登録番号を明記のこと）

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark office connected therewith (*list name and registration number*)

Karl A. Limbach	18,689	Alfred A. Equitz	30,922	Mayumi Maeda	40,075
George C. Limbach	19,305	Charles P. Sammut	28,901	Michael R. Ward	38,651
John K. Uilkema	20,282	Mark C. Pickering	36,239	Roger S. Sampson	44,314
Neil A. Smith	25,441	Patricia Coleman James	37,155	Charles L. Hamilton	42,624
Veronica C. Devitt	29,375	Kathleen A. Frost	37,326	Andrew V. Smith	43,132
Ronald L. Yin	27,607	Alan A. Limbach	39,749	Eric N. Hoover	37,355
Gerald T. Sekimura	30,103	Douglas C. Limbach	35,249	Frank J. Mycroft	P-46,946
Michael A. Stallman	29,444	Seong-Kun Oh*		Parisa Jorjani	P-46,813
Philip A. Girard	28,848	Cameron A. King	41,897	J. Thomas McCarthy	22,420
Michael J. Pollock	29,098	Kyla L. Harnel	41,815	Joel G. Ackerman	24,307
Steven M. Everett	30,050				

* Recognition under 37 CFR 10.9(b)

書類送付先

Send Correspondence to:

Charles P. Sammut, Esq.
Limbach & Limbach L.L.P.
2001 Ferry Building
San Francisco, CA 94111-4262

直接電話連絡先：（名前及び電話番号）

Direct Telephone Calls to: (*name and telephone number*)

Charles P. Sammut
(415) 433-4150

唯一または第一発明者名

Full name of sole or first inventor:

YUJI KURODA

発明者の署名

日付

Inventor's signature

Date

住所

Residence

Tokyo, Japan

国籍

Citizenship

Japan

私書箱

Post Office Address

c/o SONY CORPORATION
 7-35, Kitashinagawa 6-chome
 Shinagawa-ku, Tokyo, 141-0001 JAPAN

Japanese Language Declaration 日本語宣言書	
第二共同発明者	Full name of second joint inventor, if any KOICHIRO KISHIMA
第二共同発明者 日付	Second inventor's signature Date
住所	Residence Kanagawa, Japan
国籍	Citizenship Japan
私書箱	Post Office Address c/o SONY CORPORATION 7-35, Kitashinagawa 6-chome Shinagawa-ku, Tokyo, 141-0001 JAPAN
第三共同発明者	Full name of third joint inventor, if any ISAO ICHIMURA
第三共同発明者 日付	Third inventor's signature Date
住所	Residence Tokyo, Japan
国籍	Citizenship Japan
私書箱	Post Office Address c/o SONY CORPORATION 7-35, Kitashinagawa 6-chome Shinagawa-ku, Tokyo, 141-0001 JAPAN
第四共同発明者	Full name of fourth joint inventor, if any KIYOSHI OSATO
第四共同発明者 日付	Fourth inventor's signature Date
住所	Residence Chiba, Japan
国籍	Citizenship Japan
私書箱	Post Office Address c/o SONY CORPORATION 7-35, Kitashinagawa 6-chome Shinagawa-ku, Tokyo, 141-0001 JAPAN